

ANUCHROME – SCARLET CHROME S-47

ANUCHROME S-47 is a Molybdate Orange. It is a pre-darkened quality with yellower tone in our Scarlet Chrome range of Pigments. This is a highly stabilized pigment and offers very good fastness to light and weathering. This product, due to its excellent light fastness characteristics is strongly recommended for automotive coatings meant for refinishing purpose and also for Synthetic Enamels where better light fastness is required.

TECHNICAL DATA

Colour Index No.	77605
Colour Index Pigment No.	R-104
Oil Absorption	14-20
Specific Gravity	5.2-6.0
Bulk Density g/cc	0.93
BLEEDING IN (1-Poor 5-Excellent)	
Water	5
5% Caustic Soda	3
5% Hydrochloric Acid	3
Linseed Oil	5
Ethanol	5
Ethyl Acetate	5
Xylene	5
n-Butanol	5
Methyl Ethyl Ketone	5
Mineral Turpentine	5
Cellosolve	5
Diocetyl Phthalate	5
RESISTANCE TO HEAT	
120°C / 30 min.	SB
150°C / 20 min.	SB
180°C / 10 min.	USB
210°C / 10 min.	USB
RESISTANCE TO LIGHT	
Full Tone	8
Tint Tone (1:10)	8
RESISTANCE TO	
Acid	F
Alkali	P
APPLICATIONS	
Paints	*
Printing Inks	*
Rubber	
Leather Pastes	*
Linoleum	*
PVC Leather Cloth	*
Paper Coating	
Chalk / Crayons	

Plastics	*
----------	---

LEGEND

COLOUR	BLEEDING	HEAT STABILITY	LIGHTFASTNESS	APPLICATIONS	E – EXCELLENT
Y – YELLOW	SCALE (1-5)	SB : STABLE	SCALE (1-8)	* :RECOMMENDED/	VG – VERY GOOD
R – RED	5:NO BLEED	USB : UNSTABLE	1 – POOR	MAYBE USED	G – GOOD
W – WHITE	1:CONSIDERABLE BLEED		8 – EXCELLENT		F – FAIR
					P – POOR