CRAY VALLEY

COATING RESINS

TECHNICAL DATA — SYNOCURE 864S

SALES SPECIFICATION

Non-volatile content, % @ 150°C	58-62
Viscosity in CPS at 25°C	1800-30000
Colour, Gardner scale (ISO 4630)	≤ 1
Acid value, mg KOH/g (ISO 3682)	3 - 8

OTHER PROPERTIES

Volatile	C- 9
Non-volatile content, % @ 150°C	60
Flash point, °C (ISO 3679)	29
Density at 20°C (ISO 2811)	0.99
Hydroxyl content, %	1.5
Hydroxyl equivalent weight	1140

Note - Hydroxyl content quoted relative to solid resin

PRODUCT INFORMATION

SYNOCURE 864S is a hydroxy lfunctional acrylic resin developed for use in compliant two component systems when cured with polyisocyanate.
SYNOCURE 864S is recommended for the formulations which are crosslink at room temperature with polyisocyanate. and is particularly recommended where economy in use is a major factor. Excellent flexibility is a key feature of SYNOCURE 864S.
Characteristics of SYNOCURE 864S based coatings include:

- Economy in use
- Excellent exterior durability
- Low isocyanate demand
- Long pot life

RECOMMENDATIONS FOR USE:

REACTION RATIOS: SYNOCURE 864S should be mixed with the selected polyisocyanate just prior to application.
Stoichiometric mixing ratios are recommended to obtain optimum performance. Alternative ratios may be suitable for some applications, but should be evaluated by the coating formulator beforehand.
The reaction ratio is calculated from the respective equivalent weight or hydroxyl and isocyanate content of the reactants. The relationship is:

Equivalent weights (EqW): Hydroxyl EqW $\frac{17 \times 100}{\%\ OH}$ Isocyanate EqW $\frac{42 \times 100}{\%\ NCO}$

Conventional polyisocyanates such as Desmodur N75 [1] and Tolonate HDB75MX [2] can be used successfully

	on solid resin	as supplied
SYNOCURE 864S	1140	1900
AR - 75	242	323
N- 75	191	255

SOLVENTS: The solvents chosen for paints and lacquers based on SYNOCURE 864S should be free of water and should not contain groups that react with isocyanates.

POT LIFE: SYNOCURE 864S reacted with N-75 and AR - 75 in stoichiometric proportions has a usable pot life at spraying viscosity in excess of a full working day at normal room temperature. The use of catalysts or higher temperatures will reduce this storage period, although paints will still remain usable for several hours.

CATALYSTS: To increase the initial rate of cure of SYNOCURE 864S based paints, at both ambient temperature and under low bake conditions, the use of tin catalyst in the form of dibutyl tin dilaurate is strongly recommended. The level used will depend on specific requirements, but the recommended minimum level would be 0.001% tin calculated on total solid resin plus isocyanate.

SYNOCURE 864S should only be used in applications consistent with the above recommendations. Proposals to use the resin in other ways should be discussed with Cray Valley before any action is taken.

Notes: N – 75 From Bayer
AR – 75 From CVRIPL
UV Absorber - Cieba

The information contained in this document is based on trials carried out by our Technical centres and data selected from literature, but shall in no event be help to constitute or imply any warranty, undertaking, expressed or implied commitment from our part. Our formal specifications define the limit of our commitment. No liability whatsoever can be accepted by CRAY VALLEY with regard to the handling, processing or use of the product or products concerned which must in all cases be employed in accordance with all relevant laws and/or regulations in force in the country or countries concerned.

CRAY VALLEY (I) PVT. LTD
D-43(1) MIDC Industrial AREA Navi Mumbai - 400706
TELEPHONE: 55907102-08

ATOFINA