

COATING RESINS

TECHNICAL DATA

SYNOCURE 878S

SALES SPECIFICATION

Non-volatile content, % @ 150°C	58-62
Typical supply Viscosity, 25°C in CPS	2000-2800
Colour, Gardner scale (ISO 4630)	≤ 1
Acid value, mg KOH/g (ISO 3682)	5 - 10

OTHER PROPERTIES

Volatile	C-9
Non Volatiles	60
Flash point, °C (ISO 3679)	29
Density at 20°C (ISO 2811)	1.02
Hydroxyl content, %	2.7
Hydroxyl equivalent weight	630

Note - Hydroxyl content quoted relative to solid resin

PRODUCT INFORMATION

SYNOCURE 878S is a hydroxy functional acrylic resin developed for use in compliant two component systems when cured with polyisocyanate.

SYNOCURE 878S is recommended for the formulations which are crosslink at room temperature with polyisocyanate. and is particularly recommended specially for off-shore applications. Characteristics of SYNOCURE 878S based coatings include:

- Excellent Chemical and stain resistance
- Excellent Adhesion
- Good Durability

RECOMMENDATIONS FOR USE:

REACTION RATIOS: SYNOCURE 878S should be mixed with the selected polyisocyanate just prior to application. Stoichiometric mixing ratios are recommended to obtain optimum performance. Alternative ratios may be suitable for some applications, but should be evaluated by the coating formulator beforehand.

The reaction ratio is calculated from the respective equivalent weight or hydroxyl and isocyanate content of the reactants. The relationship is:

Equivalent weights: Hydroxyl EqW (EqW)	$\frac{17 \times 100}{\% \text{ OH}}$	Isocyanate EqW	$\frac{42 \times 100}{\% \text{ NCO}}$
--	---------------------------------------	----------------	--

Conventional polyisocyanates such as Desmodur N75 ⁽¹⁾ and Tolonate HDB75MX ⁽²⁾ can be used successfully

	on solid resin	as supplied
SYNOCURE 878S	630	1050
Tolonate HDB 75 MX ⁽²⁾	191	255
N- 75	191	255

SOLVENTS: The solvents chosen for paints and lacquers based on SYNOCURE 878S should be free of water and should not contain groups that react with isocyanates.

POT LIFE: SYNOCURE 878S reacted with Tolonate HDB-75MX ⁽²⁾ in stoichiometric proportions has a usable pot life at spraying viscosity in excess of a full working day at normal room temperature. The use of catalysts or higher temperatures will reduce this storage period, although paints will still remain usable for several hours.

CATALYSTS: To increase the initial rate of cure of SYNOCURE 878S based paints, at both ambient temperature and under low bake conditions, the use of tin catalyst in the form of dibutyl tin dilaurate is strongly recommended. The level used will depend on specific requirements, but the recommended minimum level would be 0.001% tin calculated on total solid resin plus isocyanate.

SYNOCURE 878S should only be used in applications consistent with the above recommendations. Proposals to use the resin in other ways should be discussed with Cray Valley before any action is taken.

Notes: ⁽¹⁾ Bayer ⁽²⁾ Rhodia.