

COATING RESINS

TECHNICAL DATA

SYNOCURE AC516N

SALES SPECIFICATION

Non-volatile content, % @ 150°C	58-62
Viscosity in CPS at 25°C	2200-3200
Colour, Gardner scale (ISO 4630)	≤ 2
Acid value, mg KOH/g (ISO 3682)	≤10

OTHER PROPERTIES

Volatile	C- 9
Non-volatile content, % @ 150°C	60
Flash point, °C (ISO 3679)	29
Density at 20°C (ISO 2811)	0.99
Hydroxyl content, %	2.6
Hydroxyl equivalent weight	650

Note - Hydroxyl content quoted relative to solid resin

PRODUCT INFORMATION

SYNOCUREAC516N is a hydroxy functional acrylic resin developed for use in compliant two component systems when cured with polyisocyanate.

SYNOCUREAC516N is recommended for the formulations which are crosslink at room temperature with polyisocyanate. and is particularly recommended where weatherability is a major factor. Excellent Duraibility is a key feature of SYNOCURE AC516N.

Characteristics of SYNOCURE AC516N based coatings include:

- Good Mechanical, Impact Resistance
- Good weatherability
- Excellent exterior durability
- Good Humidity and Salt Resistance
- Ideal choice for Car refinishing, Wood and Plastic

RECOMMENDATIONS FOR USE:

REACTION RATIOS: SYNOCURE AC516N could be mixed with the selected polyisocyanate just prior to application. Stoichiometric mixing ratios are recommended to obtain optimum performance. Alternative ratios may be suitable for some applications, but should be evaluated by the coating formulator beforehand.

The reaction ratio is calculated from the respective equivalent weight or hydroxyl and isocyanate content of the reactants. The relationship is:

Equivalent weights: Hydroxyl EqW (EqW)	$\frac{17 \times 100}{\% \text{ OH}}$	Isocyanate EqW	$\frac{42 \times 100}{\% \text{ NCO}}$
--	---------------------------------------	----------------	--

Conventional polyisocyanates such as Desmodur N75⁽¹⁾ or Tolonate HDB75MX⁽²⁾ can be used successfully

	on solid resin	as supplied
SYNOCURE AC516N	650	1083
Tolonate HDB75MX ⁽²⁾	191	255
N- 75	191	255

SOLVENTS: The solvents chosen for paints and lacquers based on SYNOCUREAC516N should be free of water and should not contain groups that react with isocyanates.

POT LIFE: SYNOCURE AC516 reacted with N-75 in stoichiometric proportions has a usable pot life at spraying viscosity in excess of a full working day at normal room temperature. The use of catalysts or higher temperatures will reduce this storage period, although paints will still remain usable for several hours.

CATALYSTS: To increase the initial rate of cure of SYNOCURE AC516N based paints, at both ambient temperature and under low bake conditions, the use of tin catalyst in the form of dibutyl tin dilaurate is strongly recommended. The level used will depend on specific requirements, but the recommended minimum level would be 0.001% tin calculated on total solid resin plus isocyanate.

UV ABSORBERS: To optimise the performance of SYNOCUREAC516N, when used in a clear varnish formulation, the use of Tinuvin 1130⁽³⁾ and Tinuvin 292⁽³⁾ in a 1:1 ratio is recommended.

SYNOCUREAC516N should only be used in applications consistent with the above recommendations. Proposals to use

COATING RESINS

TECHNICAL DATA

SYNOCURE AC516N

Notes: N – 75 From Bayer
TOLONATE HDB75MX from Rhodia

UV Absorber - Cieba

the resin in other ways should be discussed with Cray Valley before any action is taken.

November 2001

Page 2 of 1

UPC 99686

The information contained in this document is based on trials carried out by our Technical centres and data selected from literature, but shall in no event be help to constitute or imply any warranty, undertaking, expressed or implied commitment from our part. Our formal specifications define the limit of our commitment. No liability whatsoever can be accepted by CRAY VALLEY with regard to the handling, processing or use of the product or products concerned which must in all cases be employed in accordance with all relevant laws and/or regulations in force in the country or countries concerned.

CRAY VALLEY (I) PVT. LTD
D-43(1) MIDC Industrial AREA Navi Mumbai - 400706
TELEPHONE: 55907102-08

