

CRAY VALLEY

COATING RESINS	
TECHNICAL DATA	CRAY HARD 8001

SALES SPECIFICATIONS

%Non Volatile Content	100%
Viscosity (50% in Ethanol) in Secs.	25 – 30 Secs.
Maximum Colour in Gardner	≤12 Gardner
Acid Value.mgms KOH/g	130 - 145
Melting Point in °c	125 - 135°c

OTHER PROPERTIES

%Non Volatile Content	100%
-----------------------	------

PRODUCT INFORMATION:

CRAY HARD 8001 is a spirit soluble Rosin modified Maleic resin which is modified in combination with Glycerol.

Characteristics of CRAY HARD 8001 based coatings and inks include:

- Excellent spirit solubility.

SOLUBILITY:

It is soluble in alcohol only. It is not soluble in aromatic and aliphatic hydrocarbon.

COMPATIBILITY:

CRAYHARD 8001 is compatible with the all flexo additives.

USES:

CRAYHARD 8001 is used in all paper coating varnishes, picture varnishes and liquid inks. It can be used in ball point ink. It is also used in French polish and liquid inks.

CRAY HARD 8001 should be used in applications consistent with the above recommendations. Proposals to use the resin in other ways should be discussed with Cray Valley before any action is taken.

CRAY VALLEY RESINS INDIA LTD.

D-43 (1) Trans Thane Creek, M.I.D.C. Industrial Area, Navi Mumbai-400 706.
Tel : 022-55907102-08 Fax : 022-27687998

CRAY VALLEY RESINS INDIA LTD.

D-43 (1) Trans Thane Creek, M.I.D.C. Industrial Area, Navi Mumbai-400 706.
Tel : 022-55907102-08 Fax : 022-27687998